



# Hybond®

## PRODUCT DATA SHEET



666 Redna Terrace, Suite 600  
Cincinnati, OH 45215  
Customer Service: (800) 330-5566

**Product Number:** CF-88/ CF-88R  
**Description:** Cal & OTC Complaint Canister Contact Adhesive

### Typical Physical Properties:

<b>Adhesive</b>	Flam / Flam (Propellant / Adhesive)	<b>VOC</b>	65 g/l (EPA Method 24)
<b>Dry Time</b>	2-3 Minutes	<b>Coverage Rate</b>	3.0 dry grams/sq. ft. minimum
<b>Solvents</b>	A-70/DME/CO2	<b>Clean Up</b>	Choice Brands 689 or Citrus Cleaner
<b>Open Time</b>	30-45 minutes	<b>Shelf Life</b>	1 Year in unopened container
<b>Color</b>	Natural / Red	<b>VHAP</b>	0.00 lbs/lbs of solids
<b>Flash Point</b>	-156 deg F	<b>Pattern</b>	Web
		<b>Packaging</b>	8, 27, 128 & 252 lb



**Qualifies for LEED®-NC & CI EQ Credit 4.4: laminating adhesives shall contain no added urea formaldehyde resins**

### Properties:

- OTC & Cal Compliant, Leed Compliant 4.4: No-Urea Formaldehyde added.
- Mist spray pattern eliminates telegraphing
- Soft spray allows for greater control of pattern and application rates
- High solids means extended mileage
- Excellent Heat resistance and bond strength

### Canister Set Up and Precautions:

Attach and securely tighten a hose, in your length of choice to the matching fitting provided on the gun. Attach the other end of the hose to the matching fitting on the canister. It is recommended that plumbers tape be used on the fittings to assure an air tight seal. Check the fittings again for tightness. Slowly open the valve on the top of the canister and check for leaks. Half way is recommended at first. When hose is connected, keep canister valve open and hose pressurized at all times. Do not disconnect the hose until ready connect to new canister. Release pressure in hose before disconnecting from canister. For optimum performance, store at 70° F (21°C) during use. Canister must be above 50° F (10° C). Do not use in application plastics, expanded/extruded polystyrene, polyethylene, or polypropylene. Use only in well ventilated areas. Do not use near ignition sources with copper or aluminum components. This adhesive is not recommended for use with plasticized vinyl, flexible

## Application:

1. Prepare the surface to be bonded. Ensure both faces are clean and free of dust, dirt and grease. If necessary, wipe clean with CBA Citrus Cleaner.
2. Hold spray gun at a constant distance of between 6-10 inches (150-250mm) from the surface, allowing adhesive to cobweb across the surface with minimal overlap for thick laminates. For thin laminates allow for approximately 50% overlap of successive passes to prevent telegraphing.
3. Maintain a constant hand speed during spraying. Apply a consistent and thorough coating without allowing the adhesive to puddle or heavily wet the surface. Maximum bond strength is achieved with substrate coverage between 80-100% with a recommended coat weight minimum of 2.5-3.0 dry grams per square foot.
4. Maximum adhesion will be obtained by spraying opposing mating faces with an adhesive pattern at 90° angles to each other. (Example: Face one substrate vertically while spraying. Face the other substrate horizontally. Extra coverage is recommended at substrate edges.
5. Hold spray gun at 90° to substrate surface while spraying. Release trigger at end of each pass to optimize coverage.
6. Apply a minimum of 3.0 dry grams/sq. ft. For best results, apply two coats of adhesive to any porous surface; one base coat and a secondary top coat. This ensures adequate layup particularly on CARB 2 PARTICLEBOARD and other similar surfaces. Allow the second coat to completely dry before assembly. The adhesive should cover 80% of the surface of the substrate. The coated substrate surface should exhibit a uniform glossy sheen when the adhesive is completely dry. Dull areas indicate insufficient coverage. Adhesive should be re-applied to these areas.
7. Make sure to coat all exposed edges and corners with two coats of adhesives. Allow adhesive to dry completely before attempting assembly. (Dry time may vary due to humidity and temperature variations.) Test for dryness using back of hand only – surface should be tacky, but adhesive should not transfer to the skin.
8. Position substrates carefully and apply pressure. Work from the center of the substrate, out to prevent bubbles and wrinkles. Apply adequate pressure (40 PLI) using a nip roller. Proper use of a 3" J-roller will also provide proper pressure
9. The bonded assembly is immediately able to be trimmed or routed. Full bond strength is achieved after 24-48 hours depending on temperature and humidity.

**Storage Conditions:** Store between 60 and 90° F for best performance. Do not expose to direct sunlight. Diminished performance may occur below 60 degrees. If so, warm canister to room temperature. Remove directly from concrete floor in cold temps. Do not freeze.

**Attention:** Empty container remains hazardous until all flammable vapors, which may explode upon ignition, are gone from residue and container. Observe all labeled hazard precautions. Do not cut, puncture, or weld while hazard exists. Do not reuse empty container. Recycle, or dispose of, according to all federal, state, and local regulations.

**Use in conjunction with: Adjustable Spray Gun (part no LJC6106) w/ 80015E or 6501 Tip and hose**

**Avoid application equipment containing aluminum or copper.**

**Please Refer To The Safety Data Sheet For Further Information.**