



Hybond®

PRODUCT DATA SHEET



666 Redna Terrace, Suite 600
Cincinnati, OH 45215
Customer Service: (800) 330-5566

Product Number: **HY-36 / HY-36R**

Description: **Neoprene Contact Adhesive, Spray Grade For Flat Work**

Typical Physical Properties:

Viscosity	200 cps	VOC	578 g/l (EPA Method 24)
Dry Time	3-5 Minutes	Coverage Rate	2.0-2.5 dry grams/sq. ft. min
Solids	17% +/- 1%	Clean Up	Choice Brands 689
Open Time	30-45 minutes	Shelf Life	1 Year in unopened container
Color	Natural / Red	VHAP	2.64 lbs/lbs of solids
Solvents	Organic solvents	Density	6.6 wt/gl
Flash Point	-20 deg F	Packaging	5 gal, 54 gal and tote containers
Coverage	105-130 sq. ft./gallon		

Qualifies for LEED®-NC & CI EQ Credit 4.4: *laminating adhesives shall contain no added urea formaldehyde resins*

Properties:

- Economy flammable spray grade contact cement
- Excellent adhesion to a variety of substrates including, but not limited to laminates, particle board, plywood, hardwood, leather, rubber, and metal
- Excellent room temperature contact-ability
- Excellent green strength and high heat resistance
- Excellent spray-ability (hot or cold spraying)

Application:

1. Substrates should be clean and free of moisture, dirt, oil and other contaminants.
2. For best results, adhesive and substrates should be allowed to acclimate to room temperature (approximately 60°F or above) before adhesive application.
3. The adhesive should be applied at approximately 2.5 grams/square foot. The adhesive should cover 80% of the substrate surface. The substrate surface should exhibit a uniform glossy sheen when the adhesive is completely dry. Dull areas indicate insufficient coverage. Adhesive should be reapplied to these areas.
4. When bonding porous substrates, it is advisable to apply two coats of adhesive. The first coat will act as a sealer and prevent excessive absorption of adhesive into the substrate. After the first coat has dried, apply a second coat. Allow the second adhesive coating to dry completely before assembly.
5. Allowing the contact adhesive to dry completely before assembly is essential to obtaining a secure, permanent bond. To check for adhesive dryness, press the back of your fingers onto the adhesive surface. If adhesive transfers to fingers, additional dry time is necessary. If there is no adhesive transfer, the substrates are ready for bonding.

6. If areas exist with excessive adhesive deposition, twist the fingers while pressing them onto the adhesive layer. This will break any skin that may have formed as the adhesive dries from the top surface down. If a skin has formed, allow additional dry time to ensure complete evaporation of the solvent before bonding.
7. Dry times can be improved through the use of air movement, drying ovens, lamps, etc.
8. Substrates may be indexed together and bonded once the adhesive is dry. Bonds must be made within the open time of the adhesive. (Open times vary by adhesive. See specification)
9. Uniform pressure on the bonded laminates is necessary to create strong, lasting bonds. 40 pounds per linear inch is recommended to ensure complete fusion between the two layers of adhesive. A pinch roller is the ideal method for applying uniform pressure. When used properly, a J-roller can also provide sufficient pressure for bonding.
10. All contact adhesive bonds are immediately able to be routed, trimmed, cut, filed and machined.

Recommended Equipment:

Product Specifications				
Typical Fluid Pressure		Atomization Pressure		Spray Pattern
10-15 psi		30-50 psi		Pebble
Spray Equipment				
Binks				
<i>Manual</i>	<i>Auto</i>	<i>Fluid Tip</i>	<i>Needle</i>	<i>Air Cap</i>
95, 2100	21, 95	63ASS	663A, 563A	66SD-3
Devilbiss				
<i>Manual</i>	<i>Auto</i>	<i>Fluid Tip & Needle</i>		<i>Air Cap</i>
JGA-510, MBC-510	AGX	FX, FF		24, 797
CA Technologies				
<i>Gun</i>			<i>Set Up</i>	
Panther			1.5 x 2266-3T	
Tomcat			1.5 x 2266-3	

Application Precautions:

- Avoid application equipment containing aluminum or copper.
- Avoid copper or copper alloy substrates.
- Do not use on polystyrene foams or plasticized vinyls
- Do not mix with other adhesives. Thinning the adhesive is not recommended.

Storage Conditions:

- Rotate stock, use oldest first.
- Keep covered to prevent solvent loss and contamination.
- Do not freeze. Store product between 60 – 80°F.
- Do not store in direct sunlight.

Please Refer To The Safety Data Sheet For Further Information.

NOTICE TO PURCHASER: The information, data and suggestions for use of the materials given here are based on our best experience and knowledge, but we do not guarantee the results to be obtained in customer's processes. The products discussed are sold without any warranty regarding merchantability or fitness for a particular purpose or any other warranty express or implied. Before using, user shall determine the suitability of the product for his intended use, and user assumes all risk and liability whatsoever in connection therewith. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Sellers and manufacturers only obligation shall be to replace such quantity of the product proved to be defective. Since the manufacturer of the described in this data sheet has no means of controlling the final use of the product by the consumer or user, it is the responsibility of the immediate purchaser and any intermediate sellers to inform the user of the purposes for which the product may be fit and suitable, and of the properties of the product, including the precautionary measures which must be taken in order to insure the safety of the user and of other third persons and property.